

PAT-NO: JP02003073520A
DOCUMENT-IDENTIFIER: JP 2003073520 A
TITLE: ACRYLIC FILM AND ITS LAMINATE
PUBN-DATE: March 12, 2003 ← date no good

INVENTOR-INFORMATION:

NAME	COUNTRY
DOI, NORIHITO	N/A
MATSUMURA, YOICHI	N/A
MATSUMOTO, SHIGEMI	N/A

ASSIGNEE-INFORMATION:

NAME	COUNTRY
KANEGAFUCHI CHEM IND CO LTD	N/A

APPL-NO: JP2001220115

APPL-DATE: July 19, 2001

PRIORITY-DATA: 2001184433 (June 19, 2001)

INT-CL (IPC): C08L033/10, B32B027/30 , C08J005/18

ABSTRACT:

PROBLEM TO BE SOLVED: To provide a film causing little stress-whitening, having high surface hardness and rigidity and excellent in transparency when laminated on a plastic molding or the like.

SOLUTION: This film is obtained by molding a resin composition comprising an acrylic graft copolymer and a methacrylic graft copolymer, wherein the content of acrylic ester-based rubber-like polymer is 5-20 wt.%, the average particle diameter of the acrylic ester-based rubber-like polymer is 500-2,000 μm ; and the relation between the average particle diameter d (μm ;) and the amount w

(wt.%) of crosslinking agent used in the acrylic ester-based rubber-like polymer satisfies the formula $0.002d \leq w \leq 0.005d$, the graft rate of the acrylic graft copolymer is 30-200% and the reduced viscosity of the methyl ethyl ketone-soluble of the resin composition is 0.2-0.8 dl/g.

COPYRIGHT: (C) 2003, JPO